



Technical data sheet

LEGEND TUNG OIL / TOH-000, TOH-401 to TOH-409

DESCRIPTION

Saman Legend tung oil is a natural oil recommended for interior wood surfaces: floors, furniture, doors and windows, woodworks, etc. The oil enhances wood grain, leaves no film on the wood surface, repels dirt and resists abrasion. Saman Legend tung oil is easy to apply, low odor and easy maintenance. Available in 9 colors that can be mixed together to create other colors.

PRODUCT SPECIFICATIONS

Solids: 93-99% (by weight); 89-99% (by volume)
Viscosity: 28-32 seconds (Zahn cup #2) at 77°F
Density: 0.93-1.16 kg/l
Drying times: approximately 8-10 hours at 70°F and 50% relative humidity
Coverage: up to 300 sq. ft per liter
VOC: 7 to 85 g/l
Gloss levels: matt-satin
Recommended applicators: cotton cloth or pad
Clean up: Clean applicator and equipment with Oil and wax remover TOC-000
Storage: store in a cool, dry place. KEEP OUT OF REACH OF CHILDREN.
Shelf life: at least 1 year in a well closed container.

APPLICATION

1. Surfaces must be clean, dry and free from wax, grease, dirt and dust.
2. Sand evenly with a 100 or 120 grit sandpaper and dust off the surface.
3. Remove possible skin formed on surface and stir thoroughly before use.
4. Apply one coat of oil carefully spreading it as evenly as possible. After 5 to 15 minutes, remove excessive oil non absorbed by the wood with a cloth.
5. Let dry for 8 to 10 hours before applying a second coat by doing the same above-described procedure. Do not sand between coats.
6. For a satin finish, pass a polishing machine equipped with a polishing pad on the oiled surface.

Soak used rags and cloths in water immediately after use to prevent spontaneous combustion.

Curing

Wait 24 hours before allowing light traffic on the final coat. The curing process takes 14 to 28 days. Place rugs after two weeks.

Maintenance

Legend oiled floors and surfaces cleaner FOC-000
Legend restorer and protects FOR-000

To the best of our knowledge, the information contained herein is accurate. Since conditions and methods are beyond our control, no warranty is expressed or implied as for the final result. The user is advised to access the suitability of the product on a test area before application.